

# **MOTIVE T1275-AGM**

MODEL T1275-AGM

VOLTAGE 12

CAPACITY 132Ah @ 20Hr MATERIAL Polypropylene

BATTERY VRLA AGM / Non-Spillable / Maintenance-Free

COLOR Maroon

WATERING No Watering Required







## **12 VOLT**

#### **PHYSICAL SPECIFICATIONS**

BCI	MODEL NAME	TERMINAL TYPE G	DIMENSIONS © INCHES (mm)			WEIGHT LBS. (kg)	HANDLES	INSTALLATION ORIENTATION
2010			LENGTH	WIDTH	HEIGHT			Horizontal
GC12	T1275-AGM	M8/AP/LT	12.96 (329)	7.06 (179)	10.96 (278)	83 (38)	Embedded	and Vertical

#### **ELECTRICAL SPECIFICATIONS**

VOLTAGE	Cranking P	erformance	Capacity <sup>A</sup> Minutes		CAPACITY <sup>B</sup> AMP-HOURS (Ah)		ENERGY (kWh)	INTERNAL RESISTANCE (m $\Omega$ )	SHORT CIRCUIT CURRENT (amps)		
10	C.C.A. <sup>D</sup> @0°F	C.A. <sup>E</sup> @32°F	@ 25 Amps	@ 75 Amps	5-Hr	10-Hr	20-Hr	100-Hr	100-Hr	4.2	2020
12	_	_	254	70	114	126	132	135	1.62	4.3	2920

### **CHARGING INSTRUCTIONS**

CHARGER VOLTAGE SETTINGS (AT 77°F/25°C)					
SYSTEM VOLTAGE	12V	24V	36V	48V	
Maximum Charge Current (A)		20%	of C <sub>20</sub>		
Absorption Voltage (2.40 V/cell)	14.40	28.80	43.20	57.60	
Float Voltage (2.25 V/cell)	13.50	27.00	40.50	54.00	
	7				

Do not install or charge batteries in a sealed or non-ventilated compartment. Constant under or overcharging will damage the battery and shorten its life as with any battery.

#### **CHARGING TEMPERATURE COMPENSATION**

ADD	SUBTRACT
0.005 volt per cell for every 1°C below 25°C 0.0028 volt per cell for every 1°F below 77°F	0.005 volt per cell for every 1°C above 25°C 0.0028 volt per cell for every 1°F above 77°F

#### **OPERATIONAL DATA**

OPERATING TEMPERATURE	SELF DISCHARGE		
-4°F to 122°F (-20°C to 50°C) At temperatures below 32°F (0°C) maintain a state of charge greater than 60%	Less than 3% per month depending on storage temperature conditions		

#### **RECYCLE RESPONSIBLY**









#### **STATE OF CHARGE MEASURE OF OPEN-CIRCUIT VOLTAGE**

PERCENTAGE CHARGE	CELL	12 VOLT
100	2.14	12.84
75	2.09	12.54
50	2.04	12.24
25	1.99	11.94
0	1.94	11.64


#### TROJAN T125-AGM PERFORMANCE





#### PERCENT CAPACITY VS. TEMPERATURE




#### **BATTERY DIMENSIONS** (shown with M8)








#### SELF DISCHARGE VS. TIME"



#### **TERMINAL CONFIGURATIONS**



**M8** M8 WITH AP ADAPTER (ADAPTER PROVIDED BUT NOT INSTALLED) **Battery Height with Terminal in Inches (mm)** 11.41 (290) Torque Values in-lb (Nm) Connection to M8: 85 - 90 (10 - 11)Connection to AP: 50 - 70 (6 - 8)

- A. The number of minutes a battery can deliver when discharged at a constant rate at 80°F (27°C) and maintain a voltage above 1.75 V/cell. Capacities are
- based on peak performance.

  The amount of amp-hours (Ah) a battery can deliver when discharged at a constant rate at 80°F (27°C) for the 20-Hour rate and 86°F (30°C) for the 5-Hour rate and maintain a voltage above 1.75 V/cell. Capacities are based on peak performance.

  Dimensions may vary depending on type of handle or terminal. Batteries should be mounted with 0.5 inches (12.7 mm) spacing minimum.
- C.C.A. (Cold Cranking Amps) the discharge load in amperes which a new, fully charged battery can maintain for 30 seconds at 0°F (-18°C) at a voltage above 1.2 V/cell.
- E. C.A. (Cranking Amps) the discharge load in amperes which a new, fully charged battery can maintain for 30 seconds at 32°F (0°C) at a voltage above 1.2 CAL Clorating Arrigo Ten deschaleg level in a Imperes which a reve, may regard usually 2 and internation to 30 seconds at 32 V/Cell. This is sometimes referred to as marine craning amps @ 32°F or M.C.A. @ 32°F. Height taken from bottom of the battery to the highest point on the battery. Heights may vary depending on type of terminal. Terminal images are representative only.

- A boost charge should be performed every 6 months when batteries are in storage.
- Weight may vary.











Designed in compliance with applicable BCI, DIN, BS and IEC standards. Tested in compliance to BCI and IEC standards.

